
**Rubber compounding ingredients —
Carbon black — Determination of
high-temperature loss on heating by
thermogravimetry**

*Ingrédients de mélange du caoutchouc — Noir de carbone —
Détermination de la perte à la chaleur à haute température par
thermogravimétrie*

STANDARDSISO.COM : Click to view the full PDF of ISO 21870:2005



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 21870:2005

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 21870 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

STANDARDSISO.COM : Click to view the full PDF of ISO 21870:2005

Rubber compounding ingredients — Carbon black — Determination of high-temperature loss on heating by thermogravimetry

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard describes a method for quantitative determination of the loss on heating (pyrolysis) of carbon black due to the elimination of volatile materials other than those liberated when heating to 125 °C (ISO 1126). The method is applicable to carbon black for the rubber industry.

It serves to assess the decomposition of functional groups and adsorbed substances (e.g. hydrocarbons) present on the surface of the carbon black.

2 Principle

A known mass of carbon black is placed in the cradle of a thermobalance and heated according to a predetermined temperature programme in a controlled, oxygen-free atmosphere. The mass variation recorded provides a thermogram which can be used for quantitative evaluation.

3 Apparatus

There are several thermogravimetric measurement instruments available commercially.

The basic components are:

- 3.1 Thermobalance**, with a sensitivity of one microgram and equipped with an appropriate cradle made of a non-oxidizing material.
- 3.2 Furnace**, allowing temperature regulation from the ambient temperature up to approximately 1 000 °C.
- 3.3 Temperature programmer**, allowing a heating rate of up to 50 °C/min.
- 3.4 Nitrogen gas distributor**, associated with flow-control equipment allowing measurements in a range from 10 cm³/min to 250 cm³/min.
- 3.5 Data acquisition and processing system**.

4 Materials

- 4.1 Cylinder of compressed nitrogen** containing less than 10 ppm of oxygen.

5 Procedure

- 5.1 Power up the various elements of the analyser and preheat the furnace to 40 °C in accordance with the manufacturer's instructions.
- 5.2 Close the furnace of the thermobalance, purge with a constant, predefined flow of nitrogen (usually 100 cm³/min) in accordance with the manufacturers' instructions and maintain a constant flow for the duration of the test.
- 5.3 Wait for the thermobalance to stabilize.
- 5.4 Place the test sample in the cradle and weigh it to the nearest 0,01 mg. The sample mass should not be less than 5 mg.
- 5.5 Start the test.
- 5.6 Heat the furnace to 125 °C at a rate of 20 °C/min.
- 5.7 Maintain the temperature at 125 °C for 15 min and record the mass.
- 5.8 Heat the furnace from 125 °C to 950 °C at a rate of 20 °C/min. Due to instrumental limitations, the user may be obliged to run the test at a lower maximum temperature, e.g. at 800 °C. These conditions can lead to slightly lower test results for the loss on pyrolysis and shall therefore be mentioned in the test report.
- 5.9 Maintain the furnace at a temperature of 950 °C until the mass remains constant. A mass loss lower than 0,05 %, relative to the initial mass, during 15 min is considered as "constant mass".

6 Expression of results

Express the results as percentages of the initial mass:

$$V = \frac{m_{40} - m_{125}}{m_{40}} \times 100$$

$$P = \frac{m_{125} - m_{950}}{m_{40}} \times 100$$

where

V is the volatile matter at 125 °C (%) in nitrogen;

P is the loss on pyrolysis at 950 °C (%) in nitrogen;

m_{40} is the initial mass at 40 °C (g);

m_{125} is the mass at 125 °C (g);

m_{950} is the mass at 950 °C (g).

7 Test report

The test report shall contain the following information:

- a) all information necessary for identification of the sample tested;
- b) a reference to this International Standard (ISO 21870:2005);
- c) the type of apparatus used;
- d) the loss on heating to 125 °C (volatile matter), to the nearest 0,1 %;
- e) the loss on further pyrolysis (125 °C to 950 °C), to the nearest 0,1 %;
- f) any deviations from the procedure specified, e.g. a maximum temperature lower than 950 °C;
- g) any unusual features (anomalies) observed during the test;
- h) the date of the test.

STANDARDSISO.COM : Click to view the full PDF of ISO 21870:2005

Bibliography

- [1] ISO 1126, *Rubber compounding ingredients — Carbon black — Determination of loss on heating*

STANDARDSISO.COM : Click to view the full PDF of ISO 21870:2005