

INTERNATIONAL STANDARD

ISO
2426-3

First edition
2000-12-01

Plywood — Classification by surface appearance —

Part 3: Softwood

*Contreplaqué — Classification selon l'aspect des faces —
Partie 3: Bois résineux*

STANDARDSISO.COM : Click to view the full PDF of ISO 2426-3:2000



Reference number
ISO 2426-3:2000(E)

© ISO 2000

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 2426-3:2000

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 2426 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 2426-3 was prepared by Technical Committee ISO/TC 89, *Wood-based panels*, Subcommittee SC 3, *Plywood*.

This first edition of ISO 2426-3, together with ISO 2426-1 and ISO 2426-2, cancels and replaces ISO 2426:1974, of which it constitutes a technical revision.

ISO 2426 consists of the following parts, under the general title *Plywood — Classification by surface appearance*:

- *Part 1: General*
- *Part 2: Hardwood*
- *Part 3: Softwood*

STANDARDSISO.COM : Click to view the full PDF of ISO 2426-3:2000

Plywood — Classification by surface appearance —

Part 3: Softwood

1 Scope

This part of ISO 2426 specifies the nature and limits of characteristics inherent in wood and manufacturing defects enabling the visual assessment of the plywood for allocation to an appearance class.

This part of ISO 2426 applies to plywood, the surface veneers of which are made from softwood species. It does not apply to overlaid panels.

2 Normative reference

The following normative document contains provisions which, through reference in this text, constitute provisions of this part of ISO 2426. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 2426 are encouraged to investigate the possibility of applying the most recent edition of the normative document indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 2426-1, *Plywood — Classification by surface appearance — Part 1: General*.

3 Classification by surface appearance

3.1 Appearance classes

Assessment of characteristics and defects for determination of appearance class shall be carried out in accordance with ISO 2426-1. Surface classification shall be based on the permissible characteristics and defects within each of the appearance classes as specified in 3.2.

3.2 Permissible characteristics and defects

3.2.1 General

Each surface shall be individually assigned to one of the appearance classes E, I, II, III or IV, as defined by the permissible characteristics according to Table 1 and permissible defects according to Table 2.

3.2.2 Characteristics inherent in wood

Classification according to characteristics inherent in wood is given in Table 1.

Table 1

Categories of characteristics		Appearance class							
		E	I	II	III	IV			
3.2.2.1	Pin knots ^a	Practically absent	3/m ² permitted	Permitted					
3.2.2.2	Sound intergrown knots		Permitted up to an individual diameter of: 15 mm provided their cumulative diameter does not exceed 30 mm/m ²		50 mm 60 mm				
			Such knots may have splits provided they are very slight		slight				
3.2.2.3	Unsound or non-adhering knots and knot holes		Permitted up to an individual diameter of: 6 mm if filled and up to a number of 2/m ²		5 mm if unrepaired 25 mm if filled and up to a number of 6/m ²	40 mm			
3.2.2.4	Splits		Permitted if less than: 1/10 of panel length up to an individual width of: 3 mm			Length unlimited			
	Open		1/3 10 mm and up to a number of: 3/m			25 mm			
	Closed		1/2 15 mm 3/m of panel width if properly filled			unlimited			
	All splits greater than 2 mm in width to be filled					Permitted			
3.2.2.5	Abnormalities due to insects, marine borers and parasitic plants	Not permitted	Not permitted	Marks of parasitic plants not permitted. Insects and marine borer holes permitted up to a: diameter of 3 mm vertically to the plane of the panel up to a number of 10/m ²	width of 15 mm and length of 60 mm up to a number of 3/m ²	Permitted, but see Note			
3.2.2.6	Resin pockets and inbark		Not permitted	Permitted up to a width of: 6 mm if properly filled		Permitted, but see Note			
	Resin streaks		Not permitted	40 mm Permitted if slight		Permitted			
3.2.2.7	Irregularities in the structure of the wood	Practically absent	Permitted if very slight		if slight		Permitted		
3.2.2.8	Discoloration which is not wood-destroying		Permitted if low contrast			Permitted			
3.2.2.9	Fungal decay wood-destroying	Not permitted	Not permitted						
3.2.2.10	Other characteristics	Practically absent	To be considered under the category which they most closely resemble						
NOTE Characteristics inherent to wood are permitted provided that they do not impair the serviceability of the panel.									
a Pin knots: sound intergrown knots of no more than 3 mm diameter.									

3.2.3 Manufacturing defects

Classification according to manufacturing defects is given in Table 2.

Table 2

Categories of defect	Appearance class				
	E	I	II	III	IV
3.2.3.1 Open joints	Not permitted	Not permitted	Permitted up to a width of:		
			3 mm	10 mm	25 mm
			and up to a number of:		
			1/m	2/m	unlimited
			of panel width with joints		
			filled if more than 1 mm in width	unfilled	unfilled
3.2.3.2 Overlaps			Permitted up to a number of 1/m ² and up to 100 mm length	Permitted up to a number of 2/m ²	Permitted but see Note
3.2.3.3 Blisters			Not permitted		
3.2.3.4 Hollows, imprints and bumps			Permitted if slight	Permitted	
3.2.3.5 Roughness			Permitted if slight	Permitted	
3.2.3.6 Sanding through			Not permitted	Permitted up to an extent of:	1 %
				5 %	of panel surface
					but see Note
3.2.3.7 Glue penetration			Permitted if slight and occasional		Permitted, but see Note
			up to an extent of 5 % of the panel surface		
3.2.3.8 Foreign particles	Not permitted	Not permitted	Ferrous particles not permitted		
3.2.3.9 Repairs:	Practically without defects	Practically without defects	Permitted if properly made and tightly filled up to number of:		
1) Patches			5/m ²	unlimited	
2) Shims					
3) Synthetic fillers	Not permitted	Not permitted	Permitted within limits of the category which it most closely resembles		
3.2.3.10 Defects at the panel edges due to sanding or sawing	Practically without defects	Permitted up to:		Permitted, but see Note	
		2 mm from the edge	5 mm from the edge	5 mm from the edge	
3.2.3.11 Other defects	To be considered under the category which they most closely resemble				
NOTE Manufacturing defects are permitted provided that they do not impair the serviceability of the panel.					

Bibliography

- [1] ISO 1096, *Plywood — Classification*.
- [2] ISO 2074, *Plywood — Vocabulary*.
- [3] ISO 2426-2, *Plywood — Classification by surface appearance — Part 2: Hardwood*.

STANDARDSISO.COM : Click to view the full PDF of ISO 2426-3:2000