
**Rubber-covered rollers — Determination
of apparent hardness —**

Part 2:

Shore-type durometer method

*Cylindres revêtus de caoutchouc — Détermination de la dureté
apparente —*

Partie 2: Méthode au duromètre type Shore



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 7267-2:2008



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 7267-2 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This second edition cancels and replaces the first edition (ISO 7267-2:1986), which has been revised primarily to modify the test time (see 6.1) and to update the normative references.

ISO 7267 consists of the following parts, under the general title *Rubber-covered rollers — Determination of apparent hardness*:

- *Part 1: IRHD method*
- *Part 2: Shore-type durometer method*
- *Part 3: Pusey and Jones method*

Introduction

The hardness of a roller covering has traditionally been determined on the finished roller, since it is this hardness that is critical to the correct functioning of the roller in its end application. Values of hardness, determined by whichever method is chosen, are therefore dependent not only on the method employed and on the rubber, but also on the diameter of the roller, the thickness of the covering and, in the case of thin coverings, on the nature of the roller core. For this reason, the term “apparent hardness” is used to distinguish between the values obtained by methods described in the various parts of this International Standard and those that would be obtained for the rubber if it was possible to use the standard test methods for standard test pieces forming the subjects of other International Standards.

Since rollers vary considerably in size, construction and end use, and in view of the fact that hardness determinations are made for such different purposes as specification and factory process control, it has not been possible to standardize on one test method. Consequently, three methods are described (see Foreword), each capable of standing alone.

STANDARDSISO.COM : Click to view the full PDF of ISO 7267-2:2008

Rubber-covered rollers — Determination of apparent hardness —

Part 2: Shore-type durometer method

WARNING — Persons using this part of ISO 7267 should be familiar with normal laboratory practice. This part of ISO 7267 does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

CAUTION — Certain procedures specified in this part of ISO 7267 may involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This part of ISO 7267 specifies a method for the determination of the apparent hardness of vulcanized- or thermoplastic-rubber roller covers, expressed in Shore hardness, for measurement where only medium precision is required. The method and apparatus used are essentially those described in ISO 7619-1, the measurements in this case being made on the curved surface of the conditioned rubber-covered roller rather than on a flat test piece. Shore type A and type D instruments are specified, the latter being used for measurements on rollers of high hardness.

NOTE With some rollers, there may be significant variation in the thickness of the rubber over the surface of the roller, which could affect the measured apparent hardness.

2 References

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7619-1, *Rubber, vulcanized or thermoplastic — Determination of indentation hardness — Part 1: Durometer method (Shore hardness)*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Time interval between forming and finished grinding, and testing

Tests shall not be carried out less than 16 h after forming and/or finished grinding and, for arbitration purposes, not less than 72 h after forming.

4 Conditioning and temperature of test

Whenever possible, the test shall be carried out at a standard laboratory temperature in accordance with ISO 23529. The product under test shall, if possible, be maintained under the test conditions for sufficient time to reach temperature equilibrium with the test environment. Where this is impracticable, the period of time and the conditions shall be as given in the product specification (see Note).

The same temperature shall be used throughout any one test or series of tests intended to be comparable.

NOTE For large rollers having heavy, metal cores, ambient conditions may not allow equilibrium temperatures to be obtained.

5 Apparatus

The apparatus used shall be either the Shore type A or the Shore type D instrument described in ISO 7619-1.

Measurements shall be made with a type D instrument when values above 90 are obtained with the type A durometer, and with the type A instrument when values less than 20 are obtained with the type D durometer.

6 Procedure

6.1 Firmly locate the roller to be tested with its major axis horizontal and with the area in which the hardness is to be measured uppermost. Hold the hardness meter in position with the indenter immediately above the area which is to be measured. Apply the presser foot to the roller surface as rapidly as possible, without shock, ensuring that the indenter is normal to the rubber surface. Apply just sufficient force to obtain firm contact between the presser foot and the roller. Normally, the reading is taken 3 s after the presser foot is in firm contact with the roller surface for vulcanized rubber or 15 s after the presser foot is in firm contact with the roller surface for thermoplastic rubber. Other test times may be used, however, provided they are stated in the test report.

Better reproducibility may be obtained by using either a stand or mass centred on the axis of the indenter, or both, to apply the presser foot to the test piece. Masses of 1 kg and 5 kg are recommended for type A and type D durometers, respectively.

6.2 Make three measurements at different points at least 6 mm apart within the test area in which the hardness is to be determined.

NOTE Several test areas along the length and around the circumference of the roller may be required to determine the average hardness of the covering and the hardness variation over a single roller (see ISO 6123-1, *Rubber or plastics covered rollers — Specifications — Part 1: Requirements for hardness*).

7 Expression of results

Express the apparent hardness as the median of the three measurements for each test area, reported to the nearest whole number in Shore A or Shore D units.