

<p>NOTICE OF ADOPTION</p>

ADOPTION NOTICE 1
25 October 1994
AMS 2405B
1 October 1984

Society of Automotive Engineers Aerospace Material Specification AMS 2405B was adopted on 25 October 1994 and is approved for use by the Department of Defense (DoD). Copies of the document are stocked at the Standardization Documents Order Desk, Bldg. 40, 700 Robbins Avenue, Philadelphia PA 19111-5094, for issue to DoD activities only. Other Government activities, contractors, private concerns, or other requestors must obtain the document from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale PA 15096-0001, or some other authorized distributor.

Title of Document: Electroless Nickel Plating Low Phosphorus

Date of Specific Issue Adopted: 1 October 1984

Release Non-Government Standards Body: Society of Automotive Engineers

NOTE: Use AMS 2404C, AMS 2405B, and AMS 2433A in lieu of MIL-C-26074.

Custodians:

Air Force - 11
 Army - MR
 Navy - AS

Military Coordinating Activity:

Air Force - 11

(Project No. MFFP- 0528)

Reviewers:

Air Force - 68, 84, 99
 Navy - SH
 Army - MI, AR

Users:

Navy - OS
 Army - ME

AMSC N/A

AREA MFFP

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited..

SAE The Engineering
Resource For
Advancing Mobility®

400 COMMONWEALTH DRIVE WARRENDALE PA 15096

AEROSPACE
MATERIAL
SPECIFICATION

AMS 2405B
Superseding AMS 2405A

Issued 2-15-65
Revised 10-1-84

ELECTROLESS NICKEL PLATING
Low Phosphorus

1. SCOPE:

- 1.1 Purpose: This specification covers the engineering requirements for electroless deposition of low-phosphorus nickel on various materials and the properties of the deposit.
- 1.2 Application: Primarily to provide hard, ductile, wear-resistant, and corrosion-resistant surfaces for operation up to 1000°F (540°C) and to provide uniform build-up on complex shapes. Maximum hardness and wear resistance are obtained by heating parts as in 3.3.2.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B117 - Salt Spray (Fog) Testing

ASTM B487 - Measurement of Metal and Oxide Coating Thicknesses by Microscopical Examination of a Cross Section

ASTM E290 - Semi-Guided Bend Test for Ductility of Metallic Materials

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

AMS 2405B

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Preparation:

- 3.1.1 Welding and brazing shall be completed before parts are plated, unless surfaces are plated to aid in joining by brazing.
- 3.1.2 Surfaces of metal parts to be plated shall be smooth and substantially free from blemishes, pits, tool marks, and other irregularities.
- 3.1.3 Surfaces of nonmetallic parts shall show no marks other than those necessary to provide a freshly-abraded surface.
- 3.1.4 Parts having hardness higher than 40 HRC and which have been machined or ground after heat treatment shall be suitably stress-relieved before cleaning for plating. Temperatures to which parts are heated shall be such that maximum stress-relief is obtained without reducing hardness of parts below drawing limits.
- 3.1.5 Parts shall have chemically clean surfaces, prepared with minimum abrasion, erosion, or pitting, prior to immersion in the plating solution.

3.2 Procedure:

- 3.2.1 Plating shall be performed by chemical deposition of an amorphous, high-nickel, low-phosphorus metallic compound on a catalytic or catalyzed surface from an aqueous bath containing nickel and hypophosphite ions and which bath may include a soluble compound to inhibit decomposition of the bath. The nickel-phosphorus plate shall, unless otherwise specified, be deposited directly on the basis metal without a deposit of other metal underneath except in the case of parts fabricated from corrosion-resistant steels or alloys on which a preliminary deposit of nickel or other suitable metal is permissible.
- 3.2.2 The plated parts shall be removed from the plating solution, thoroughly rinsed, and dried.

3.3 Post Treatment:

- 3.3.1 After plating, rinsing, and drying, parts shall be heat treated as in 3.3.1.1, 3.3.1.2, or 3.3.1.3 unless they are to be post treated as in 3.3.2 or unless otherwise permitted to remove hydrogen embrittlement; heating shall be in air, preferably in a circulating-air furnace.

AMS 2405B

- 3.3.1.1 Parts, including roll-threaded parts, cold worked after being heat treated by hardening and tempering, springs, and other parts having hardness of 33 HRC or over, shall be heated to $375^{\circ}\text{F} \pm 15$ ($190^{\circ}\text{C} \pm 8$) and held at heat for not less than 3 hours.
- 3.3.1.2 Parts and assemblies, including carburized parts, which will decrease in hardness or be otherwise deleteriously affected by heating to 375°F (190°C) shall be heated to $275^{\circ}\text{F} \pm 15$ ($135^{\circ}\text{C} \pm 8$) and held at heat for not less than 5 hours.
- 3.3.1.3 Parts requiring special handling shall be treated as agreed upon by purchaser and vendor.
- 3.3.2 When specified on the drawing, parts, after plating, rinsing, and drying, shall be heated for 30 - 60 min., preferably in an inert atmosphere, at $750^{\circ}\text{F} \pm 15$ ($400^{\circ}\text{C} \pm 8$) except that parts made of aluminum or aluminum alloy shall be heated at $450^{\circ}\text{F} \pm 15$ ($230^{\circ}\text{C} \pm 8$) for not less than 4 hours.
- 3.4 Properties: Plating shall conform to the following requirements:
- 3.4.1 Composition: The phosphorus content of the deposited nickel-phosphorus alloy shall be held as low as possible and shall not exceed 8%.
- 3.4.2 Thickness: Shall be as specified on the drawing, determined on representative parts or test panels by micrometer method, by microscopic method in accordance with ASTM B487, or by other method agreed upon by purchaser and vendor.
- 3.4.3 Adhesion: Specimens shall show no separation of plating from the basis metal, when examined at up to 6X magnification, after being bent rapidly at room temperature, in accordance with ASTM E290, through an angle of 180 deg around a diameter equal to the nominal thickness of the specimen. Formation of cracks which do not result in flaking or blistering of the plating is acceptable.
- 3.4.3.1 As a referee test, plating shall show no blisters or cracks on representative steel parts or test panels after being heated in air, preferably in a circulating-air furnace, at $700^{\circ}\text{F} \pm 15$ ($370^{\circ}\text{C} \pm 8$) for 23 hr ± 1 followed by heating at $1000^{\circ}\text{F} \pm 15$ ($540^{\circ}\text{C} \pm 8$) for 60 min. ± 5 .
- 3.4.4 Corrosion Resistance: Steel parts or representative test panels having specified minimum plating thickness of 0.001 in. (25 μ) or more, shall, after plating and embrittlement-relieving, show no visual evidence of corrosion of the basis metal after being subjected for not less than 48 hr to continuous salt spray corrosion test conducted in accordance with ASTM B117.
- 3.5 Quality: Plated surfaces shall be smooth, continuous, and uniform in appearance and shall be free from frosty areas, pinholes, blisters, and other imperfections detrimental to usage of the plate.

AMS 2405B

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The processing vendor shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that processing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for thickness (3.4.2) and quality (3.5) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for composition (3.4.1), adhesion (3.4.3) and corrosion resistance (3.4.4) and of cleaning and plating solutions to ensure that the deposited metal will conform to the requirements of this specification are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of plated parts to a purchaser, when a change in material or processing, or both, requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be not less than the following:

4.3.1 For Acceptance Tests:

4.3.1.1 Thickness: Three parts for each consecutive 8 hr of operation of the same set of solutions, except as specified in 4.3.3.

4.3.1.2 Quality: As agreed upon by purchaser and vendor.

4.3.2 For Periodic Tests and Preproduction Tests: As agreed upon by purchaser and vendor.