

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

AMS 3108A

Issued 7-1-48

Revised 12-1-51

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

## PRIMER, OCHER Phenolic

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. TYPE: Semi-gloss baking yellow-tan.

3. APPLICATION: As a prime coating on metal surfaces before enameling.

4. COMPOSITION:

4.1 Product, by Weight:

Non-Volatile	60% min
Volatile	40% max

4.1.1 Non-Volatile:

Resin	48-50%
Pigment	50-52%

4.1.1.1 Resin: Shall be a thermosetting phenolic type with softening agenda added; It shall be free from rosin, rosin derivatives, oils and cellulose derivatives.

4.1.1.2 Pigment: Shall be a natural ocher.

4.1.2 Volatile: Shall be an organic solvent composed of one or more of the following types of compounds: alcohols, esters, hydrocarbons and ketones.

5. TECHNICAL REQUIREMENTS:

5.1 General: Primer shall be of uniform consistency, and free from bubbles, grit rough particles, floating or caked pigments, and ingredients of respiratory toxicity under normal conditions of use. Component ingredients shall be intimately mixed, and processed as required to produce a product which is stable and not subject to abnormal change with age in sealed containers.

5.2 Coarse Particles: Not more than 0.1% by weight of the primer shall be retained on a No. 325 screen.

5.3 Flash Point, Tag Closed Tester: Shall be not lower than 60 F.

5.4 Viscosity: Shall be 9-13 poises absolute at 77 F not less than 24 hr after manufacture.

5.5 Skinning and Livering: Shall be absent in a 1/4-filled closed container after standing one week.

5.6 Color: Shall be yellow-tan, characteristic of ocher.