

**AEROSPACE
MATERIAL
SPECIFICATION**Issued NOV 2004
Reaffirmed JUN 2006**Type 8**
Virgin Polytetrafluoroethylene (PTFE) Moldings or Extrusions with 10% Carbon
Fiber**1. SCOPE:****1.1 Form:**

This specification covers a polytetrafluoroethylene (PTFE) resin filled with carbon fiber in the form of extruded or molded rods or tubes which are sintered after molding or, in the case of extrusions, sintered during the extrusion process.

1.2 Application:

These products have been used typically for parts such as backup rings and seal elements in both static and dynamic applications requiring dimensional stability up to 450 °F (232 °C) with good mechanical properties, but usage is not limited to such applications. Each application should be considered individually.

2. APPLICABLE DOCUMENTS:

See AMS 3678.

3. TECHNICAL REQUIREMENTS:**3.1 Basic Specification:**

The complete requirements for procuring the products described herein shall consist of this document and the latest issue of the basic specification, AMS 3678.

3.2 Material:

All products shall be molded or extruded from virgin polytetrafluoroethylene (PTFE) powder conforming to ASTM D 4894, Type II or Type IV, and should contain 10% \pm 1 of carbon fibers dispersed throughout the material. The Carbon fibers should be a commercial grade of carbon fibers.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790

Email: custsvc@sae.org
<http://www.sae.org>

SAE WEB ADDRESS: