

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE

AMS 4035J

Issued
Revised

JUN 1940
SEP 1996

Superseding AMS 4035H

ALUMINUM ALLOY, SHEET AND PLATE
4.4Cu - 1.5Mg - 0.60Mn (2024-0)
Annealed

UNS A92024

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of sheet and plate.

1.2 Application:

These products have been used typically for formed structural parts which will be subsequently heat treated, but usage is not limited to such applications.

1.2.1 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking after heat treatment; ARP823 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings

MAM 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1996 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

2.1 (Continued):

AMS 2770 Heat Treatment of Wrought Aluminum Alloy Parts

AMS 2811 Identification, Aluminum and Magnesium Alloy Wrought Products

ARP823 Minimizing Stress-Corrosion Cracking in Wrought Heat-Treatable Aluminum Alloy Products

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-H-6088 Heat Treatment of Aluminum Alloys

2.4 ANSI Publications:

Available from American National Standards Institute, Inc., 11 West 42nd Street, New York, NY 10035-8002.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS:**3.1 Composition:**

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition

Element	min	max
Copper	3.8	4.9
Magnesium	1.2	1.8
Manganese	0.30	0.9
Iron	--	0.50
Silicon	--	0.50
Zinc	--	0.25
Titanium	--	0.15
Chromium	--	0.10
Other impurities, each	--	0.05
Other impurities, total	--	0.15
Aluminum	remainder	

3.2 Condition:

Annealed in accordance with MIL-H-6088.

3.3 Properties:

The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 As Annealed (O Temper):

3.3.1.1 Tensile Properties: Shall be as shown in Table 2.

TABLE 2A - Tensile Properties, Inch/Pound Units

Nominal Thickness Inches	Tensile Strength ksi, max	Yield Strength At 0.2% Offset ksi, max	Elongation in 2 Inches or 4D %, min
0.010 to 0.499, incl	32.0	14.0	12
Over 0.499 to 1.750, incl	32.0	--	12

TABLE 2B - Tensile Properties, SI Units

Nominal Thickness Millimeters	Tensile Strength MPa, max	Yield Strength At 0.2% Offset MPa, max	Elongation in 50.8 mm or 4D %, min
0.25 to 12.67, incl	221	96	12
Over 12.67 to 44.45, incl	221	--	12

3.3.1.2 Bending: Product shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 3 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 3 - Bending Parameters

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
0.010 to 0.032, incl	0.25 to 0.81, incl	0
Over 0.032 to 0.063, incl	Over 0.81 to 1.60, incl	1
Over 0.063 to 0.128, incl	Over 1.60 to 3.25, incl	4
Over 0.128 to 0.499, incl	Over 3.25 to 12.67, incl	6

3.3.2 Response to Heat Treatment: The product, as received by purchaser, shall have the following properties after being solution heat treated in accordance with AMS 2770 and aging for not less than 4 days at room temperature to the -T42 temper:

3.3.2.1 Tensile Properties: Shall be as shown in Table 4.
(R)

TABLE 4A - Minimum Tensile Properties, Inch/Pound Units

Nominal Thickness Inches	Tensile Strength Ksi	Yield Strength At 0.2% Offset ksi	Elongation in 2 Inches or 4D %
0.010 to 0.020, incl	62.0	38.0	12
Over 0.020 to 0.249, incl	62.0	38.0	15
Over 0.249 to 0.499, incl	62.0	38.0	12
Over 0.499 to 1.000, incl	61.0	38.0	8
Over 1.000 to 1.500, incl	60.0	38.0	7
Over 1.500 to 1.750, incl	60.0	38.0	6

TABLE 4B - Minimum Tensile Properties, SI Units

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength At 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
0.25 to 0.51, incl	427	262	12
Over 0.51 to 6.32, incl	427	262	15
Over 6.32 to 12.67, incl	427	262	12
Over 12.67 to 25.40, incl	421	262	8
Over 25.40 to 38.10, incl	414	262	7
Over 38.10 to 44.45, incl	414	262	6

- 3.3.2.2 Bending:** Product shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 5 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 5 – Bending Requirements

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
0.010 to 0.020, incl	0.25 to 0.51, incl	4
Over 0.020 to 0.051, incl	Over 0.51 to 1.30, incl	5
Over 0.051 to 0.128, incl	Over 1.30 to 3.25, incl	6
Over 0.128 to 0.249, incl	Over 3.25 to 6.32, incl	8
Over 0.249 to 0.499, incl	Over 6.32 to 12.67 incl	10

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

(R)

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

(R)

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), tensile properties as annealed (3.3.1.1) and after

(R)

solution heat treatment and aging (3.3.2.1), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each inspection lot.

4.2.2 Periodic Tests: Bending as annealed (3.3.1.2) and after solution heat treatment and aging (3.3.2.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

(R)

Shall be in accordance with AMS 2355 or MAM 2355.