



AEROSPACE MATERIAL SPECIFICATION

AMS4146™**REV. H**

Issued	1960-06
Noncurrent	2005-02
Reaffirmed	2014-05
Revised	2021-07

Superseding AMS4146G

Aluminum Alloy Forgings and Rolled or Forged Rings and Forging Stock
1.0Mg - 0.60Si - 0.28Cu - 0.20Cr (6061 - T4)
Solution Heat Treated and Naturally Aged
(Composition similar to UNS A96061)

RATIONALE

AMS4146H results from a Five-Year Review and update of this specification with changes to prohibit unauthorized exceptions (3.6, 4.4.3, 8.5), condition (3.2), tensile properties (3.3.1.2.1, 8.4), and ordering information (8.6).

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of die forgings up to 4 inches (102 mm), hand forgings up to 8 inches (203 mm), rolled or forged rings up to 2.5 inches (63.5 mm) in thickness, and forging stock (see 8.6).

1.2 Application

These products have been used typically for parts which will be welded or brazed to assemblies and then given further heat treatment to develop the full strength of which the alloy is capable, but usage is not limited to such applications.

1.2.1 Corrosion resistance of this alloy is generally superior to that of aluminum alloys containing copper as a principal alloying element.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2021 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS4146H>

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2201	Tolerances, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled or Cold Finished
AMS2355	Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings
AMS2645	Fluorescent Penetrant Inspection
AMS2770	Heat Treatment of Wrought Aluminum Alloy Parts
AMS2772	Heat Treatment of Aluminum Alloy Raw Materials
AMS2808	Identification, Forgings
ARP1917	Clarification of Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B594	Ultrasonic Inspection of Aluminum-Alloy Products for Aerospace Applications
ASTM B660	Packing/Packaging of Aluminum and Magnesium Products

2.3 ANSI Accredited Publications

Copies of these documents are available online at <http://webstore.ansi.org/>.

ANSI H35.1/H35.1M Alloy and Temper Designation System For Aluminum

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight as shown in Table 1, determined in accordance with AMS2355.

Table 1 - Composition

Element	Min	Max
Silicon	0.40	0.8
Iron		0.7
Copper	0.15	0.40
Manganese		0.15
Magnesium	0.8	1.2
Chromium	0.04	0.35
Zinc		0.25
Titanium		0.15
Others, Each		0.05
Others, Total		0.15
Aluminum	remainder	

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Die Forgings, Hand Forgings, and Rolled Rings

Solution heat treated in accordance with AMS2772 and naturally aged.

3.2.2 Forging Stock

As ordered by the forging manufacturer.

3.3 Properties

The product shall conform to the following requirements, determined in accordance with AMS2355.

3.3.1 Die Forgings, Hand Forgings, and Rolled Rings

3.3.1.1 As Solution Heat Treated and Naturally Aged to the T4 Condition (refer to ANSI H35.1/H35.1M)

3.3.1.1.1 Hardness

Shall be 50 to 80 HB/10/500 or 55 to 85 HB/10/1000, but product shall not be rejected on the basis of hardness if tensile properties after precipitation heat treatment meet all requirements of 3.3.1.2.1.

3.3.1.2 Response to Temper Conversion

Shall be as follows after being precipitation heat treated to T62 temper in accordance with AMS2770:

3.3.1.2.1 Tensile Properties

Shall be as follows:

3.3.1.2.1.1 Test Specimens

Specimens machined from separately forged coupons or from stock representing the forgings and, in either case, heat treated with the forgings, shall have the properties in Table 2:

Table 2A - Tensile properties, inch/pound units (see 8.3)

Property	Minimum
Tensile Strength	38.0 ksi
Yield Strength at 0.2% Offset	35.0 ksi
Elongation in 4D	10%

Table 2B - Tensile properties, SI units (see 8.3)

Property	Minimum
Tensile Strength	262 MPa
Yield Strength at 0.2% Offset	241 MPa
Elongation in 4D (50 mm)	10%
Elongation in 5D	9%

3.3.1.2.1.2 Die Forgings

3.3.1.2.1.2.1 With Grain Flow

Specimens, machined from forgings 4 inches (102 mm) and under in nominal thickness with axis of specimen in area of gage length varying not more than 15 degrees from parallel to forging flow lines, shall have properties specified in Table 2, except that elongation may be as low as 7% when measured in 4D, or 6% when tested with a 5D specimen (see 8.3).

3.3.1.2.1.2.2 Across Grain Flow

Specimens, machined from forgings 4 inches (102 mm) and under in nominal thickness with axis of specimen area of gage length varying not more than 15 degrees from perpendicular to forging flow lines, shall have properties specified in Table 2, except that elongation may be as low as 5% when measured in 4D, or 4% when tested with a 5D specimen (see 8.3).

3.3.1.2.1.3 Hand Forgings

Specimens machined from forgings 8 inches (203 mm) and under in nominal thickness shall have properties specified in Table 3; tests need not be made in the longitudinal direction unless specifically required by purchaser.

Table 3A - Tensile properties, inch/pound units (see 8.3)

Nominal Thickness Inches	Specimen Orientation	Tensile Strength ksi, min	Yield Strength at 0.2% Offset ksi, min	Elongation in 2 Inches or 4D %, min
Up to 4, incl	Longitudinal	38.0	35.0	10
	Long Trans.	38.0	35.0	8
	Short Trans.	37.0	33.0	5
Over 4 to 8, incl	Longitudinal	37.0	34.0	8
	Long Trans.	37.0	34.0	6
	Short Trans.	35.0	32.0	4

Table 3B - Tensile properties, SI units (see 8.3)

Nominal Thickness Millimeters	Specimen Orientation	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 5D (5.65√A) %, min
Up to 102, incl	Longitudinal	262	241	9
	Long Trans.	262	241	7
	Short Trans.	255	228	4
Over 102 to 203, incl	Longitudinal	255	234	7
	Long Trans.	255	234	5
	Short Trans.	241	221	3

3.3.1.2.1.4 Rolled Rings

3.3.1.2.1.4.1 Tangential

Specimens, machined from rings 2.50 inches (63.5 mm) and under in nominal thickness with axis of specimen tangential to ring OD (axis parallel to direction of rolling), shall have properties specified in Table 2.

3.3.1.2.1.4.2 Axial

Specimens, machined from rings 2.50 inches (63.5 mm) and over in nominal thickness with axis of specimen approximately parallel to axis of the ring (axis transverse to direction of rolling), shall have properties as specified in Table 2, except that elongation may be as low as 8% when measured in 4D, or 7% when measured with a 5D specimen (see 8.3).

3.3.1.2.1.5 Other Forgings

Tensile property requirements for die forgings, hand forgings, and rolled rings having nominal thickness greater than specified above shall be as agreed upon by purchaser and vendor.

3.3.1.2.2 Hardness

Should be not lower than 80 HB/10/500 or 85 HB/10/1000 but the product shall not be rejected on the basis of hardness if the applicable tensile property requirements are met.

3.3.1.3 Grain flow of die forgings, except in area which contains flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.3.2 Forging Stock

When a sample of stock is forged to a test coupon having a degree of mechanical working not greater than the forging and heat treated in the same manner as forgings, specimens taken from the heat treated coupon shall conform to the requirements of Table 2 and 3.3.1.2.2. If specimens taken from the stock after heat treatment in the same manner as forgings conform to the requirements of Table 2 and 3.3.1.2.2, the tests shall be accepted as equivalent to tests of a forged coupon.

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.1 Each die forging and, when specified, each rolled or forged ring shall be etched to produce a surface suitable for visual inspection. Surfaces shall be evaluated for defects such as seams, laps, bursts, and quench cracks. Surface imperfections which can be removed so that they do not reappear on re-etching and the required section thickness can be maintained are acceptable.

3.4.1.1 When approved by purchaser, a sampling plan may be used in lieu of etching each forging.

3.4.2 When specified, die forgings, hand forgings, and rolled forged rings shall be subjected to fluorescent penetrant inspection in accordance with AMS2645, to ultrasonic inspection in accordance with ASTM B594, or to both. Standards for acceptance shall be as established by purchaser.

3.5 Tolerances

Forging stock shall conform to all applicable requirements of AMS2201.

3.6 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.3.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.