

AEROSPACE MATERIAL SPECIFICATION

Issued	JAN 1983
Reaffirmed	MAY 1995
Noncurrent	FEB 1996
Cancelled	MAY 2006

Superseding AMS 4187B

Bars, and Rods, Rolled, Drawn, or Cold Finished
5.6Zn - 2.5Mg - 1.6Cu - 0.23Cr
Annealed

UNS A97075

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of May, 2006. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications indicating that it has been "CANCELLED".

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of AMS 4187C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:

Tel: 877-606-7323 (inside USA and Canada)

Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: custsvc@sae.org

SAE WEB ADDRESS:

<http://www.sae.org>

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of bars, rods, and wire.

1.2 Application: Primarily for parts requiring forming and as stock for flash welded rings which are to be subsequently solution and precipitation heat treated. Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking after solution and precipitation heat treatment; ARP 823 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) and Aerospace Recommended Practices (ARP) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2201 - Tolerances, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled or Drawn

AMS 2350 - Standards and Test Methods

AMS 2355 - Quality Assurance Sampling and Testing of Aluminum-Base and Magnesium-Base Alloys, Wrought Products (Except Forgings and Forging Stock) and Flash Welded Rings

AMS 2770 - Heat Treatment of Aluminum Alloy Parts

2.1.2 Aerospace Recommended Practices:

ARP 823 - Minimizing Stress-Corrosion Cracking in Wrought Heat-Treatable Aluminum Alloy Products

2.2 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.2.1 Military Specifications:

MIL-H-6088 - Heat Treatment of Aluminum Alloys

2.2.2 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355:

	min	max
Zinc	5.1	- 6.1
Magnesium	2.1	- 2.9
Copper	1.2	- 2.0
Chromium	0.18	- 0.28
Iron	-	0.50
Silicon	-	0.40
Manganese	-	0.30
Titanium	-	0.20
Other Impurities, each	-	0.05
Other Impurities, total	-	0.15
Aluminum	remainder	

3.2 Condition: Annealed in accordance with MIL-H-6088.

3.3 Properties: The product shall conform to the following requirements, determined in accordance with AMS 2355:

3.3.1 As Annealed:

3.3.1.1 Tensile Properties: Product 8 in. (200 mm) and under in nominal diameter or distance between parallel sides shall have the following properties:

Tensile Strength, max	40,000 psi (275 MPa)
Elongation in 2 in. (50 mm) or 4D, min	10%

3.3.1.1.1 Tensile property requirements for product over 8 in. (200 mm) in nominal diameter or distance between parallel sides shall be as agreed upon by purchaser and vendor.

3.3.2 After Solution and Precipitation Heat Treatment: Rods 4 in. (100 mm) and under in nominal diameter; square, hexagonal, and octagonal bar 3-1/2 in. (90 mm) and under in nominal thickness; and rectangular bar 3 in. (75 mm) and under in nominal thickness and 6 in. (150 mm) and under in nominal width or 10 in. (250 mm) and under in nominal width when nominal thickness is under 3 in. (75 mm), and wire shall have the following properties after solution and precipitation heat treatment in accordance with AMS 2770 to the T62 temper:

3.3.2.1 Tensile Properties:

Tensile Strength, min	77,000 psi (530 MPa)
Yield Strength at 0.2% Offset, min	66,000 psi (455 MPa)
Elongation in 2 in. (50 mm) or 4D, min	7%

- 3.3.2.2 Hardness: Should be not lower than 135 HB/10/500 or 140 HB/10/1000 but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.3.2.1 are met.
- 3.3.2.3 Tensile property and hardness requirements for bars and rods exceeding the size limits of 3.3.2 shall be as agreed upon by purchaser and vendor.
- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2201.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties as annealed (3.3.1.1) and after solution and precipitation heat treatment (3.3.2.1), and tolerances (3.5) are classified as acceptance tests and shall be performed on each lot.
- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for hardness after solution and precipitation heat treatment (3.3.2.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.