

AEROSPACE MATERIAL SPECIFICATION

Issued JAN 1992

Cancelled JUL 2005

Superseding AMS 4227D

Aluminum Alloy, Casting, Sand,
8.0Cu 6.0Mg 0.50Mn 0.50Ni,
As Cast

UNS A12400

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of July 2005. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications indicating that it has been 'CANCELLED'.

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of AMS 4227E

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2005 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:

Tel: 877-606-7323 (inside USA and Canada)

Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: custsvc@sae.org

SAE WEB ADDRESS:

<http://www.sae.org>

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of sand castings.

1.2 Application: Primarily for components operating up to 500°F (260°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods
AMS 2360 - Room Temperature Tensile Properties of Castings
AMS 2635 - Radiographic Inspection
AMS 2645 - Fluorescent Penetrant Inspection
AMS 2646 - Contrast Dye Penetrant Inspection
AMS 2694 - Repair Welding of Aerospace Castings
AMS 2804 - Identification, Castings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B557 - Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products
ASTM B660 - Packaging/Packing of Aluminum and Magnesium Products
ASTM E10 - Brinell Hardness of Metallic Materials
ASTM E21 - Elevated Temperature Tension Tests of Metallic Materials
ASTM E34 - Chemical Analysis of Aluminum and Aluminum Alloys
ASTM E155 - Reference Radiographs for Inspection of Aluminum and Magnesium Castings

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E34 or by spectrochemical or other analytical methods approved by purchaser:

	min	max
Copper	7.0	- 9.0
Magnesium	5.5	- 6.5
Manganese	0.30	- 0.7
Nickel	0.30	- 0.7
Iron	--	0.50
Silicon	--	0.50
Titanium	--	0.20
Zinc	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

- 3.2 Condition: As cast.

- 3.3 Casting: Castings shall be produced in lots from metal conforming to 3.1. Metal remelted from previously analyzed ingot may be poured directly into castings. Furnace or ladle additions of grain-refining elements or alloys are permissible. Molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted into ingot, analyzed, and remelted or unless the composition of a sample taken after the last addition to the melt conforms to 3.1.

- 3.3.1 A melt shall be the metal withdrawn from a batch-furnace charge of 2000 lb (900 kg) or less as melted for pouring castings or, when permitted by purchaser, a melt shall be 4000 lb (1800 kg) or less of metal withdrawn from one continuous furnace in not more than eight consecutive hours.

- 3.3.2 A lot shall be all castings poured from a single melt in not more than eight consecutive hours.

- 3.4 Cast Test Specimens: Chemical analysis specimens and tensile specimens shall be cast as follows and, when requested, shall be supplied with the castings:

- 3.4.1 Chemical Analysis Specimens: Shall be cast from each melt and shall be of a size and shape agreed upon by purchaser and vendor.

3.4.2 Tensile Specimens: Shall be cast with each lot of castings, shall be of standard proportions conforming to ASTM B557 with 0.500 inch (12.70 mm) diameter at the reduced parallel gage section, and shall be cast to size in molds made with the regular foundry mix of sand, without using chills. Metal for the specimens shall be part of the melt which is used for the castings. If the metal for castings is given any treatment, such as fluxing or cooling and reheating, the metal for the specimens shall be a portion of the metal so treated and, during such treatment, shall be heated to the same maximum temperature and held for approximately the same time as the molten metal for the castings. The temperature of the metal during pouring of the specimens shall be not lower than that during pouring of the castings.

3.5 Properties: Castings and representative tensile specimens produced in accordance with 3.4.2 shall conform to the following requirements:

3.5.1 Tensile Properties:

3.5.1.1 At Room Temperature: Shall be as follows, determined in accordance with ASTM B557; conformance to the requirements of 3.5.1.1.1 shall be used as basis for acceptance of castings except when purchaser specifies that the requirements of 3.5.1.1.2 apply:

3.5.1.1.1 Separately-Cast Specimens:

Tensile Strength, minimum 29,000 psi (200 MPa)

3.5.1.1.2 Specimens Cut From Castings: The lowest of not less than four, and preferably 10, specimens cut from thick and thin sections shall be as follows:

Tensile Strength, minimum 21,750 psi (150 MPa)

3.5.1.1.2.1 When properties other than those of 3.5.1.1.2 are required, tensile specimens as in 4.3.4 taken from locations indicated on the drawing, from a casting or castings chosen at random to represent the lot, shall have the properties indicated on the drawing for such specimens. Property requirements may be designated in accordance with AMS 2360.

3.5.1.2 At 400°F (205°C): Shall be as follows, determined in accordance with ASTM E21 on separately-cast specimens heated to 400°F ± 5 (205°C ± 3), held at heat for 10 to 20 minutes before testing, and tested at 400°F ± 5 (205°C ± 3) at a rate not greater than 0.05 inch/inch per minute (0.05 mm/mm per minute) up to the yield strength and at a rate of 0.11 - 0.14 inch/inch per minute (0.11 - 0.14 mm/mm per minute) above the yield strength:

Tensile Strength, minimum	27,000 psi (185 MPa)
Yield Strength at 0.2% Offset, minimum	24,000 psi (165 MPa)

3.5.2 Hardness of Castings: Castings, except at sprue and riser locations, should have hardness not lower than 80 HB/10/500 or 85 HB/10/1000, determined in accordance with ASTM E10, but castings shall not be rejected on the basis of hardness if the tensile property requirements of 3.5.1.1.2 are met.

3.6 Quality:

3.6.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings.

3.6.1.1 Castings shall have smooth surfaces and shall be well cleaned.

3.6.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.6.3 When specified, castings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645, to contrast dye penetrant inspection in accordance with AMS 2646, or to both.

3.6.4 Radiographic, fluorescent penetrant, contrast dye penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E155 may be used to define radiographic acceptance standards.

3.6.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.

3.6.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding in accordance with AMS 2694.

3.6.6 Castings shall not be impregnated, chemically treated, or coated to prevent leakage unless specified or allowed by written permission of purchaser, designating the method to be used.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Except as specified in 4.2.1.1, tests to determine conformance to requirements for composition (3.1), room-temperature tensile properties (3.5.1.1.1 or 3.5.1.1.2), hardness (3.5.2), and quality (3.6) are classified as acceptance tests and shall be performed to represent each melt or lot as applicable.

4.2.1.1 Tensile properties of specimens cut from castings shall be determined only when specified by purchaser or when separately-cast specimens are not available. Tensile properties of separately-cast specimens need not be determined when tensile properties of specimens cut from castings are determined.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for elevated-temperature tensile properties (3.5.1.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the first-article shipment of a casting to a purchaser, when a change in material, processing, or both requires reapproval, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 At least one chemical analysis specimen in accordance with 3.4.1 from each melt or a casting from each lot.

4.3.2 Three separately-cast tensile specimens in accordance with 3.4.2 from each lot except when purchaser requires properties of specimens cut from castings

4.3.3 Two preproduction castings in accordance with 4.4.1 of each part number.

4.3.4 One or more castings from each lot when properties are required from specimens machined from castings. Specimens shall conform to ASTM B557 and shall be either 0.500 in. (12.50 mm) diameter at the reduced parallel gage section, subsize specimens proportional to the standard, or standard sheet-type specimens. For determining conformance to the requirements of 3.5.1.1.2.1, if specimen locations are not shown on the drawing, not less than four tensile specimens, two from the thickest section and two from the thinnest section, shall be cut from a casting or castings from each lot.

4.4 Approval:

- 4.4.1 Sample castings from new or reworked patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.
- 4.4.2 Vendor shall establish for production of sample castings of each part number parameters for the process control factors which will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. If necessary to make any change in parameters for the process control factors, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, sample castings, test specimens, or both. Production castings incorporating the revised operations shall not shipped prior to receipt of reapproval.
- 4.4.2.1 Control factors for producing castings include, but are not limited to, the following:
- Ø
- Type of furnace
 - Furnace atmosphere
 - Gating and risering practices
 - Fluxing or deoxidation procedure
 - Metal pouring temperature; variation of $\pm 50^{\circ}\text{F}$ ($\pm 30^{\circ}\text{C}$) from the established limit is permissible
 - Solidification and cooling procedures
 - Cleaning operations
 - Methods of inspection
- 4.4.2.1.1 Any of the above process control factors for which parameters are considered proprietary by the vendor may be assigned a code designation. Each variation in such parameters shall be assigned a modified code designation.

4.5 Reports:

- 4.5.1 The vendor of castings shall furnish with each shipment a report showing the results of the test for chemical composition of at least one casting or of separately-cast specimens from each melt, the results of tests for tensile properties of separately-cast specimens representing each lot or of specimens cut from castings from each lot, and the results of tests for hardness of castings from each lot. This report shall include the purchase order number, lot number, AMS 4227C, part number, and quantity.
- 4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4227C, contractor or other direct supplier of castings, part number, and quantity. When castings for making parts are produced or purchased by the parts vendor, that vendor shall inspect each lot of castings to determine conformance to the requirements of this specification and shall include in the report either a statement that the castings conform or copies of laboratory reports showing the results of tests to determine conformance.