

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 4291B

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave. New York 17, N.Y.

Issued 10-1-43
Revised 11-1-59

ALUMINUM ALLOY CASTINGS, DIE (5Si or 8.5Si) - 3.5Cu As Cast

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. COMPOSITION:

	Composition 1	Composition 2
Silicon	4.5 - 5.5	7.5 - 9.5
Copper	3.0 - 4.0	3.0 - 4.0
Iron	1.3 max	1.3 max
Zinc	1.0 max	1.0 max
Nickel	0.50 max	0.50 max
Manganese	0.50 max	0.50 max
Tin	0.30 max	0.30 max
Magnesium	0.10 max	0.10 max
Other Impurities, total	0.50 max	0.50 max
Aluminum	remainder	remainder

2.1 Unless otherwise specified, either Composition 1 or Composition 2 may be supplied.

3. CONDITION: As cast.

4. TECHNICAL REQUIREMENTS:

4.1 Casting: Castings shall be produced in lots from metal conforming to Section 2. Metal remelted from previously analyzed ingot may be poured directly into castings. Furnace or ladle additions of small amounts of grain refining elements or alloys are permissible. Unless otherwise agreed upon by purchaser and vendor, \emptyset molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted to ingot, analyzed, and remelted or until the composition of a sample taken after the last addition to the melt has been found to conform to Section 2.

4.1.1 A melt shall be the metal withdrawn from a batch furnace charge of 2000 lb or less as melted for pouring castings or, when permitted by purchaser, a melt \emptyset shall be 4000 lb or less of metal withdrawn from one continuous furnace in not more than 8 consecutive hours.

4.1.2 A lot shall consist of castings poured from a single melt in not more than 8 \emptyset consecutive hours.

4.2 Test Specimens: Chemical analysis specimens, when required by purchaser, shall \emptyset be cast from each melt and shall be of size and shape agreed upon by purchaser and vendor.