

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



AMS 4297

Issued

OCT 1998

Aluminum Alloy Sheet
4.4Cu - 1.5Mg - 0.60Mn (2024; -T4 Flat Sheet)
Solution Heat Treated, High Formability

UNS A92024

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of sheet.

1.2 Application:

This sheet has been used typically for formed structural parts of moderate strength, but usage is not limited to such applications.

1.2.1 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking; ARP823 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1998 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:

(724) 772-7154
(724) 776-4970

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- AMS 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
- MAM 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units
- AMS 2772 Heat Treatment of Aluminum Alloy Raw Materials
- ARP823 Minimizing Stress-Corrosion Cracking in Wrought Heat-Treatable Aluminum Alloy Products

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

- ASTM B 666/B 666M Identification Marking of Aluminum and Magnesium Products

2.3 ANSI Publications:

Available from ANSI, 11 West 42nd Street, New York, NY 10036-8002.

- ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products
- ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Tables 1, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition

| Element | min | max |
|-------------------------|-----------|------|
| Copper | 3.8 | 4.9 |
| Magnesium | 1.2 | 1.8 |
| Manganese | 0.30 | 0.9 |
| Iron | -- | 0.50 |
| Silicon | -- | 0.50 |
| Zinc | -- | 0.25 |
| Titanium | -- | 0.15 |
| Chromium | -- | 0.10 |
| Other Impurities, each | -- | 0.05 |
| Other Impurities, total | -- | 0.15 |
| Aluminum | remainder | |

3.2 Condition:

Solution heat treated in accordance with AMS 2772.

3.3 Properties:

The sheet shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties: Shall be as shown in Table 2.

TABLE 2A - Minimum Tensile Properties, Inch/Pound Units

| Nominal Thickness Inch | Tensile Strength ksi | Yield Strength at 0.2% Offset ksi | Elongation in 2 inches or 4D % |
|---------------------------|----------------------------|---|--------------------------------------|
| Over 0.020 to 0.128, incl | 62 | 40 | 15 |

TABLE 2B - Minimum Tensile Properties, SI Units

| Nominal Thickness Millimeters | Tensile Strength MPa | Yield Strength at 0.2% Offset MPa | Elongation in 50.8 mm or 4D % |
|----------------------------------|----------------------------|---|-------------------------------------|
| Over 0.51 to 3.25, incl | 425 | 276 | 15 |

- 3.3.2 Bending: Sheet shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 3 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 3 - Bending Parameters

| Nominal Thickness Inch | Nominal Thickness Millimeters | Bend Factor |
|---------------------------|----------------------------------|-------------|
| Over 0.020 to 0.051, incl | Over 0.51 to 1.30, incl | 2 |
| Over 0.051 to 0.128, incl | Over 1.30 to 3.25, incl | 4 |

3.4 Quality:

Product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the sheet shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: All tests are acceptance tests and, except for composition, shall be performed on each lot.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2355 or MAM 2355.

4.4 Reports:

The vendor of sheet shall furnish with each shipment a report stating that the sheet conforms to the chemical composition, and tolerances and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot number, AMS 4297, size, and quantity.