

2545512 0074586 207

SAE-AMS4816

ADOPTION NOTICE

SAE-AMS4816, "Bearings, Silver-Clad Steel Strip", was adopted on 15-AUG-95 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Defense Industrial Supply Center, 700 Robbins Avenue, Philadelphia, PA 19111-5096. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers Inc., 400 Commonwealth Drive, Warrendale, PA 15096-0001.

Custodians:

Army - AV
Navy - AS
Air Force - 11
DLA - IS

Adopting Activities:

DLA - IS

SAENORM.COM : Click to view the full PDF of am4816b

FSC 3120

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

AMS 4816B

Issued 3-1-55
Revised 4-1-87

Superseding AMS 4816A

BEARINGS, SILVER-CLAD STEEL STRIP

1. SCOPE:

1.1 Form: This specification covers a low-alloy steel strip clad on one or both faces with silver in the form of bearing stock or finished bearings.

1.2 Application: Primarily for shims, thrust washers, bushings, and bearings.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels

AMS 2350 - Standards and Test Methods

AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock

AMS 2800 - Identification, Finished Parts

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

ASTM E378 - Spectrograph Analysis of Silver by the Powder Technique

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

3.1.1 Basis Steel: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	0.11	0.17
Manganese	0.75	1.00
Silicon	0.15	0.35
Phosphorus	--	0.040
Sulfur	--	0.040
Chromium	0.40	0.60
Nickel	0.40	0.70
Molybdenum	0.15	0.25

3.1.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.1.2 Cladding: Shall be oxygen-free silver having a minimum fineness of 99.95%, determined by spectrographic methods in accordance with ASTM E378 or by other analytical methods agreed upon by purchaser and vendor.

3.2 Condition: Shall be a composite material produced by bonding silver sheet to one or both faces of steel strip by a controlled combination of temperature and pressure and subsequently cold rolled to the specified thickness.

3.3 Properties: Bearings shall conform to the following requirements, determined in accordance with ASTM A370:

3.3.1 Hardness: The basis steel shall have hardness of 26 - 38 HRC, or equivalent.

3.3.2 Bending: Bearings, after being annealed in a suitable protective atmosphere, shall withstand, without cracking, free bending through an angle of 180 deg around a diameter equal to the nominal thickness of the bearing with axis of bend parallel to the direction of rolling and with the clad surface on the outside of bend.

3.4 Quality: Bearings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the bearings.

3.4.1 Cladding shall be firmly and continuously bonded to the steel backing, determined by a procedure agreed upon by purchaser and vendor.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of bearings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the bearings conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling: Shall be in accordance with the following; a lot shall be all bearings of one size and configuration made from a single heat of basis steel and a single heat of cladding processed in one continuous run and presented for vendor's inspection at one time:

4.3.1 Basis Steel: AMS 2370.

4.3.2 Cladding: Two samples from each heat of material melted at the same time.

4.3.3 Bearings or Bearing Stock: Three samples from each lot.

4.4 Reports:

4.4.1 The vendor of bearings shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for hardness and bending of each lot. This report shall include the purchase order number, lot number, AMS 4816B, part number, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4816B, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.