

AEROSPACE MATERIAL

AMS 5082A

Superseding AMS 5082

Issued 11/1/44
Revised 11/1/69

Society of Automotive Engineers, Inc.

TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

STEEL TUBING, SEAMLESS 0.31 - 0.38C (SAE 1035)

- 1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase order.
- 2. APPLICATION: Primarily for parts requiring a material of moderate strength.
- 3. COMPOSITION:

		min	max
	Carbon	0.31 -	0.38
Ø	Manganese	0.60 -	0.90
	Silicon	0.15 -	0.30
	Phosphorus		0.040
	Sulfur		0.050

- 3.1 <u>Check Analysis</u>: Composition variations shall meet the requirements of the latest issue of AMS 2259, paragraph titled "Carbon Steels, Seamless Tubing."
- 4. CONDITION: Unless otherwise ordered, tubing shall be supplied cold drawn and stress relieved,
- having a uniform, fine grain in all parts of the tubing.
- Ø 5. TECHNICAL REQUIREMENTS:
 - 5.1 <u>Tensile Properties</u>: Tubing having OD not over 1.5 in. with wall thickness not over 0.125 in. shall conform to the following requirements:

Tensile Strength, psi 90,000 min

Yield Strength at 0.2% Offset or at 0.0087 in.

in 2 in. Extension Under Load, (E = 30,000,000), psi 70,000 min

Elongation, % in 2 in.

Nominal OD up to 0.500 in., incl, with wall thickness

up to 0.035 in., inclusive 8 min

Nominal OD over 0.500 in. with wall thickness

over 0.035 in. 10 min

over 0.035 in.

- 5.1.1 Tubing with dimensions not shown in 5.1 shall have tensile properties as agreed upon by purchaser \emptyset and vendor.
- 5.2 <u>Tensile Properties</u>: When so ordered, tubing shall be supplied having the following tensile properties: