

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 5541

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 7-1-57
Revised

ALLOY SHEET, CORROSION AND HEAT RESISTANT
Nickel Base - 15.5Cr - 7Fe - 2.5Ti - 0.7Al

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for parts requiring high strength up to 1500 F and oxidation resistance up to 1800 F. Parts may be formed and then heat treated to improve strength at elevated temperatures.
3. COMPOSITION:

Carbon	0.08 max
Manganese	1.0 max
Silicon	0.7 max
Sulfur	0.01 max
Chromium	14.0 - 17.0
Nickel + Cobalt	70.0 min
Cobalt, if determined	1.0 max
Titanium	2.0 - 2.75
Aluminum	0.40 - 1.0
Iron	5.0 - 9.0
Copper	0.50 max

4. CONDITION: Cold rolled, annealed, descaled, and leveled.

5. TECHNICAL REQUIREMENTS:

- 5.1 Tensile Properties:

Nominal Thickness Inch	Tensile Strength psi, max	Elongation % in 2 in. min
0.025 to 0.250	125,000	40

- 5.1.1 For widths 9 in. and over, tensile test specimens shall be taken with the axis perpendicular to the direction of rolling. For widths less than 9 in., tensile test specimens shall be taken with the axis parallel to the direction of rolling.
- 5.2 Bending: Material shall withstand, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to the nominal thickness of the material, with axis of bend parallel to the direction of rolling.

5.3 Properties After Precipitation Heat Treatment: Material shall, after precipitation heat treating at $1300\text{ F} \pm 25$ for 16 hr and air cooling, be capable of meeting the following requirements:

5.3.1 Tensile Properties:

Tensile Strength, psi	140,000 min
Yield Strength at 0.2% Offset or at 0.0100 in. in 2 in. Extension Under Load ($E = 30,000,000$), psi	90,000 min
Elongation, % in 2 in.	20 min

5.3.1.1 For widths 9 in. and over, tensile test specimens shall be taken with the axis perpendicular to the direction of rolling. For widths less than 9 in., tensile test specimens shall be taken with the axis parallel to the direction of rolling.

5.3.2 Hardness: Shall be not lower than Rockwell C 23 or equivalent.

5.4 Grain Size: The average grain diameter shall be not larger than 0.0060 in. (Grain Size No. 2.5) when determined in accordance with ASTM E112-55T.

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances for widths 4 1/4 in. and under and thicknesses 0.025 in. and over shall conform to the latest issue of AMS 2262 as applicable. Thickness tolerances shall conform to Table I and width tolerances shall conform to 4.1.

8. REPORTS:

8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and the results of tests on each thickness from each heat to determine conformance to the technical requirements of this specification. This report shall include the purchase order number, heat number, material specification number, thickness, size, and quantity from each heat.

8.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.