



Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AEROSPACE MATERIAL SPECIFICATION

AMS 5562A

Superseding AMS 5562

Issued 6-1-74

Revised 7-15-80

UNS S21900

STEEL TUBING, SEAMLESS, CORROSION AND HEAT RESISTANT
9.0Mn - 20Cr - 6.5Ni - 0.28N

1. SCOPE:

- 1.1 Form: This specification covers a corrosion and heat resistant steel in the form of seamless tubing.
- 1.2 Application: Primarily for fluid-conducting lines requiring both corrosion and heat resistance, especially when such parts and assemblies are welded or brazed during fabrication, and having higher strength than that of the 18-8 types. Parts and assemblies requiring oxidation resistance up to 1100°F (595°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2243 - Tolerances, Corrosion and Heat Resistant Steel Tubing
AMS 2248 - Chemical Check Analysis Limits, Wrought Heat and Corrosion Resistant Steels and Alloys
AMS 2350 - Standards and Test Methods
AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products
ASTM A708 - Detection of Susceptibility to Intergranular Corrosion in Severely Sensitized Austenitic Stainless Steel
ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.04
Manganese	8.00 -	10.00
Silicon	--	1.00
Phosphorus	--	0.060
Sulfur	--	0.030
Chromium	19.00 -	21.50
Nickel	5.50 -	7.50
Nitrogen	0.15 -	0.40
Molybdenum	--	0.75
Copper	--	0.50

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

- 3.2 Condition: Solution heat treated and descaled.

- 3.3 Fabrication: Tubing shall be produced by a seamless process. The external and internal surface finishes may be produced by pickling, bright annealing, or any method which will provide the required surface condition and which will not affect limits of wall thickness or corrosion resistance, with the exception that centerless ground finish is not acceptable. A light polish to improve surface appearance may be employed. Passivation treatment shall follow any surface treatment used.

- 3.4 Properties: Tubing shall conform to the following requirements:

- 3.4.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM A370:

Ø Tensile Strength, min	90,000 psi (621 MPa)
Yield Strength at 0.2% Offset, min	50,000 psi (345 MPa)
Elongation in 2 in. (50 mm), min	
Strip Specimens	40%
Full Tube Specimens	45%

- 3.4.2 Flareability: Specimens as in 4.3.1 from tubing 0.125 to 2.000 in. (3.18 to 50.80 mm), incl, in nominal OD shall withstand flaring at room temperature, without formation of cracks or other visible defects, by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74-deg included angle to produce a flare having a permanent expanded OD not less than shown in Table I.

TABLE I

Nominal OD Inches	Expanded OD Inches, min	Nominal OD Inches	Expanded OD Inches, min
0.125	0.200	0.750	0.937
0.188	0.290	1.000	1.187
0.250	0.359	1.250	1.500
0.312	0.421	1.500	1.721
0.375	0.484	1.750	2.106
0.500	0.656	2.000	2.356
0.625	0.781		

TABLE I (SI)

Nominal OD Millimetres	Expanded OD Millimetres	Nominal OD Millimetres	Expanded OD Millimetres
3.18	5.08	19.05	23.80
4.78	7.37	25.40	30.15
6.35	9.12	31.75	38.10
7.92	10.69	38.10	43.71
9.52	12.29	44.45	53.49
12.70	16.66	50.80	59.84
15.88	19.84		

- 3.4.2.1 Tubing with nominal OD between any two standard sizes given in 3.4.2 shall take the same percentage flare as shown for the larger of the two sizes.
- 3.4.2.2 Flarability requirements for tubing under 0.125 in. (3.18 mm) or over 2.000 in. (76.20 mm) in nominal OD shall be as agreed upon by purchaser and vendor.
- 3.4.3 Pressure Test: The tubing shall show no bulges, leaks, pinholes, cracks, or other defects when subjected to an internal hydrostatic pressure (P), except that a diametric permanent set of 0.002 in. per in. (0.002 mm/mm) of diameter is acceptable. The hydrostatic pressure (P) shall be determined from the equation:

$$P = S \frac{D^2 - d^2}{D^2 + d^2}$$

where, P = Test Pressure in psi (MPa)
 S = Yield Strength from 3.4.1
 D = Nominal OD
 d = Nominal ID

- 3.4.4 Embrittlement: Tubing, after being sensitized by heating to 1250°F ± 25 (675°C ± 15) in air, holding at heat for 60 min. ± 5, and cooling in air, shall withstand exposure for 24 hr ± 0.25 to copper sulfate/sulphuric acid solution in accordance with ASTM A708 without evidence of inter-crystalline surface attack. After exposure, full cross-sectional specimens of tubing 0.625 in. (15.88 mm) and under in nominal OD shall be flattened to a total thickness under load of three times the wall thickness of the tubing and 1 in. (25 mm) long specimens of tubing over 0.625 in. (15.88 mm) in nominal OD shall be split and bent 180 deg, with outside surface of tube on inside of bend, around a diameter equal to the nominal wall thickness without showing cracks or other defects. In either flattening or bending, the fold shall be made parallel to the axis of the tube.

3.5 Quality:

- 3.5.1 Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice or high quality aircraft tubing. It shall be smooth, clean, and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other injurious conditions. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness but removal of such surface imperfections is not required.
- 3.5.2 Tubing shall be free from grease or other foreign matter. No metallic flakes or particles shall be collected by a clean white cloth when it is drawn through the length of the bore of a test sample. Discoloration of the cloth, without the presence of flakes or grit, is acceptable.

3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight tubing will be acceptable in mill lengths of 6 - 20 ft (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).

3.7 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2243.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform such confirmatory testing as he deems necessary to ensure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.4.1), pressure test (3.4.3), and tolerances (3.7) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for flarability (3.4.2) and embrittlement (3.4.4) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2371 and the following:

4.3.1 Specimens for flarability (3.4.2) test shall be full tubes or sections cut from tubes. The end of the specimen to be flared shall be cut square, with the cut and smooth and free from burrs, but not rounded.

4.4 Reports:

4.4.1 The vendor of tubing shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and the results of tests for tensile properties, pressure test, and tolerance requirements of this specification of each lot. This report shall include the purchase order number, heat number, AMS 5562A, size, and quantity from each heat.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 5562A, contractor or other direct supplier of tubing, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification, and shall include in the report a statement that the tubing conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Tubing shall be identified as follows: