

**AEROSPACE
MATERIAL
SPECIFICATION**

Submitted for recognition as an American National Standard

SAE AMS 5674C

Issued 5-1-69
Revised 4-1-86

Superseding AMS 5674B

STEEL WIRE, CORROSION AND HEAT RESISTANT
18Cr - 11.5Ni - 0.70 (Cb+Ta) (SAE 30347)

UNS S34700

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant steel in the form of wire.

1.2 Application: Primarily for screening and stitching applications, requiring good corrosion resistance and which will be subjected to elevated temperatures during fabrication or in service. Wire has satisfactory oxidation resistance up to 1500°F (815°C) but is useful at that temperature only when stresses are low.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

MAM 2241 - Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	17.00 -	19.00
Nickel	9.00 -	12.00
Columbium + Tantalum	10xC -	1.10
Molybdenum	--	0.75
Copper	--	0.50

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

- 3.2 Condition: Solution heat treated free from continuous carbide network and bright finished.

- 3.3 Properties: Wire shall conform to the following requirements:

- 3.3.1 Tensile Properties: Shall be as specified in Table I, determined in accordance with ASTM A370:

TABLE I

Nominal Diameter Inch	Tensile Strength, psi, max	
	Coils	Straight Lengths
Up to 0.020, incl	125,000	135,000
Over 0.020 to 0.125, incl	115,000	125,000
Over 0.125	105,000	115,000

3.3.1 (Continued):

TABLE I (SI)

Nominal Diameter Millimetres	Tensile Strength, MPa, max	
	Coils	Straight Lengths
Up to 0.50, incl	860	930
Over 0.50 to 3.00, incl	795	860
Over 3.00	725	795

3.3.2 Bending: Wire shall withstand, without cracking, bending flat on itself.

3.4 Quality: Wire, as received by purchaser, shall be uniform in quality and condition, cylindrical, and free from kinks, twists, scrapes, splits, cold shuts, and other imperfections detrimental to usage of the wire.

3.4.1 The surface shall have a bright, smooth finish free from pits, abrasions, and other defects.

3.5 Tolerances: Shall conform to all applicable requirements of AMS 2241 or MAM 2241.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling: Shall be in accordance with AMS 2371.

4.4 Reports:

4.4.1 The vendor of wire shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile and bending properties of each lot. This report shall include the purchase order number, heat number, AMS 5674C, size, and quantity from each heat.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 5674C, contractor or other direct supplier of wire, part number, and quantity. When wire for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of wire to determine conformance to the requirements of this specification and shall include in the report either a statement that the wire conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Coils or reels of wire shall each be identified with a durable tag marked with the purchase order number, AMS 5674C, heat number, nominal size, quantity, and manufacturer's identification. Straight lengths shall be bundled or boxed and shall have attached to each container a durable tag marked as above.

5.2 Packaging:

5.2.1 Wire shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the wire to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.2.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-163, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.2.1 will be acceptable if it meets the requirements of Level C.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS: Wire not conforming to this specification or to modifications authorized by purchaser will be subject to rejection.

8. NOTES:

8.1 Marginal Indicia: The phi (ϕ) symbol is used to indicate technical changes from the previous issue of this specification.

8.2 Dimensions and properties in inch/pound units are primary; dimensions and properties in SI units are shown as the approximate equivalents of the primary units and are presented only for information.