



AEROSPACE MATERIAL SPECIFICATION

AMS5835™**REV. D**

Issued 1984-07
Revised 2015-12
Reaffirmed 2021-05

Superseding AMS5812C

Nickel Alloy, Corrosion and Heat-Resistant, Welding Wire
72Ni - 3.2Mn - 20Cr - 2.5Cb - 0.48Ti
Vacuum Induction Melted, Environment Controlled Packaging
(Composition similar to UNS N06082)

RATIONALE

AMS5835D revises Fabrication (3.4.2) and Length (3.7.2), and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant nickel alloy in the form of welding wire.

1.2 Application

This wire has been used typically as filler metal for gas-tungsten-arc or gas-metal-arc welding of nickel-chromium alloys, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2269	Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys
AMS2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS2814	Packaging and Marking of Packages of Welding Wire, Premium Quality
AMS2816	Identification Welding Wire, Tab Marking Method

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2021 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS5835D>

AMS2819	Identification, Welding Wire Direct Color Code System
ARP1313	Determination of Trace Elements in High Temperature Alloys
ARP1876	Weldability Test for Weld Filler Metal Wire
ARP4926	Alloy Verification and Chemical Composition Inspection of Welding Wire

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Wire shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E354, by spectrochemical methods, or by other analytical methods acceptable to purchaser except that selenium, lead, and bismuth shall be determined in accordance with ARP1313, and oxygen and nitrogen shall be determined by Leco Analyzer or equivalent.

Table 1 - Composition

Element	min	max
Carbon	--	0.03
Manganese	3.00	3.50
Silicon	--	0.10
Phosphorus	--	0.010
Sulfur	--	0.007
Chromium	18.00	22.00
Nickel	67.00	--
Columbium	2.00	3.00
Titanium	0.20	0.75
Cobalt	--	0.10
Tantalum	--	0.30
Aluminum	--	0.10
Boron	--	0.001
Iron	--	1.00
Copper	--	0.25
Tin	--	0.005
Lead	--	0.001 (10 ppm)
Bismuth	--	0.0002 (2 ppm)
Selenium	--	0.0006 (6 ppm)
Magnesium	--	0.05
Oxygen (3.1.1)	--	0.0050 (50 ppm)
Nitrogen (3.1.1)	--	0.010 (100 ppm)

3.1.1 Except for nitrogen and oxygen, chemical analysis of initial ingot, bar or rod stock before drawing is acceptable provided the processes used for drawing or rolling, and for annealing and cleaning are controlled to ensure continued conformance to chemical composition requirements. Nitrogen and oxygen shall be determined at finished diameter.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS2269. No variation is permitted for lead, bismuth, selenium, oxygen, and nitrogen.

3.2 Melting Practice

Alloy shall be vacuum induction melted; it may be multiple melted using consumable electrode practice in the remelt cycle but remelting is not required.

3.3 Condition

Cold drawn, bright finish, in a temper which will provide proper feeding of the wire in machine welding equipment.

3.4 Fabrication

3.4.1 Wire shall be formed from rod or bar descaled by a process which does not affect the composition of the wire. Surface irregularities inherent with a forming process that do not tear the wire surfaces are acceptable provided the wire conforms to the tolerances of 3.7.

3.4.2 Butt welding is permissible only at diameters larger than final finished product size provided both ends to be joined are alloy verified using a method capable of distinguishing the alloy from all other alloys processed in the facility, or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding.

3.4.3 In-process annealing, if required, between cold rolling or drawing operations, shall be performed in vacuum or protective atmospheres to ensure freedom from surface oxidation and absorption of other extraneous elements.

3.4.4 Residual elements, drawing compounds, oxides, dirt, oil, dissolved gasses, and other foreign materials picked up during wire processing that can adversely affect the welding characteristics, the operation of the equipment, or the properties of the weld metal, shall be removed by cleaning processes that will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.5 Properties

Wire shall conform to the following requirements:

3.5.1 Weldability

Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.5.2 Spooled Wire

Shall conform to 3.5.2.1 and 3.5.2.2.

3.5.2.1 Cast

Wire, wound on standard 12 inch (305 mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length to form one loop with a nominal 1 inch (25 mm) overlap when cut from the spool and laid on a flat surface, shall form a circle 15 to 50 inches (381 to 1270 mm) in diameter.

3.5.2.2 Helix

The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).

3.6 Quality

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.7 Sizes and Tolerances

Wire shall be supplied in the sizes and to the tolerances shown in 3.7.1 and 3.7.2.

3.7.1 Diameter

Shall be as shown in Table 2.

Table 2A - Sizes and diameter tolerances, inch/pound units

Form	Nominal Diameter Inch	Tolerance Inch Plus	Tolerance Inch Minus
Cut Lengths	0.030, 0.035, 0.045	0.001	0.002
Cut Lengths	0.062, 0.078, 0.094, 0.125, 0.156, 0.187	0.002	0.002
Spools	0.007, 0.010, 0.015	0.0005	0.0005
Spools	0.020, 0.030, 0.035, 0.045, 0.062	0.001	0.002
Spools	0.078, 0.094	0.002	0.002

Table 2B - Sizes and diameter tolerances, SI units

Form	Nominal Diameter Millimeters	Tolerance Millimeter Plus	Tolerance Millimeter Minus
Cut Lengths	0.76, 0.89, 1.14	0.025	0.05
Cut Lengths	1.57, 1.98, 2.39, 3.18, 3.96,	0.05	0.05
Spools	4.75	0.013	0.013
Spools	0.18, 0.25, 0.38	0.025	0.05
Spools	0.51, 0.76, 0.89, 1.14, 1.57 1.98, 2.39	0.05	0.05

3.7.2 Length

Cut lengths shall be furnished in 18, 27, or 36-inch (457, 686, or 914 mm) lengths, or other lengths when specified by purchaser, and shall not vary more than +0, -0.5 inch (-13 mm) from the length ordered.