

AEROSPACE MATERIAL SPECIFICATION

AMS 7705E

Issued JUL 1957
Revised FEB 2006

Superseding AMS 7705D

Nickel-Iron Magnetic Alloy, Bars and Forgings

RATIONALE

AMS 7705E is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a magnetic nickel-iron alloy in the form of bars, forgings, and forging stock.

1.2 Application

These products have been used typically in magnetic circuits requiring high magnetic permeability at low flux densities after high temperature annealing in hydrogen, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2241	Tolerances, Corrosion and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS 2808	Identification, Forgings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 596 Direct-Current Magnetic Properties of Materials Using Ballistic Method and Ring Specimens
ASTM A 773 DC Magnetic Properties of Materials Using Ring and Permeameter Procedures with DC Electronic Hysteresisgraphs
ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall be a metallic alloy containing approximately 80% nickel plus iron and other alloying elements, usually copper and chromium or molybdenum, in such proportions as will provide a product meeting the requirements of 3.3.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Bars

Annealed (See 8.2) and descaled.

3.2.2 Forgings

As ordered.

3.2.3 Forging Stock

As ordered by the forging manufacturer.

3.3 Properties

The product shall conform to the following requirements:

3.3.1 Bars and Forgings

3.3.1.1 Hardness

Bars and forgings, after being annealed, shall have hardness not higher than 75 HRB, or equivalent (See 8.3), determined in accordance with ASTM E 18.

3.3.1.2 Magnetic Properties

Shall be as shown in Table 1, determined in accordance with ASTM A 596 or ASTM A 773 on specimens as in 4.3.3 annealed by heating, in a dry hydrogen atmosphere having a dew point of -60 °F (-51 °C) or lower, to 2150 °F ± 25 (1177 °C ± 14), holding at heat for 4 hours ± 0.25, and cooling in a non-contaminating atmosphere to 800 °F (427 °C) or below at a rate not greater than 100 F (56 C) degrees per hour or at a cooling rate recommended by the alloy producer (see 8.2).

TABLE 1 – Annealed Minimum Magnetic Properties

Property	Value
Maximum permeability	175,000
Permeability at 100 gauss (0.01T)	42,000
Induction at 100 oersteds (7958 A/m), gauss	7,500 (0.75T)

3.3.2 Forging Stock

As agreed upon by purchaser and vendor.

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances

Bars shall conform to all applicable requirements of AMS 2241.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing

Shall be as follows:

4.3.1 Bars and Forging Stock

In accordance with AMS 2371.

4.3.2 Forgings

In accordance with AMS 2374.

4.3.3 For magnetic property tests, one or more samples shall be selected at random from each lot.

4.4 Reports

The vendor of the product shall furnish with each shipment a report showing the results of tests for the three Table 1 magnetic properties and hardness of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 7705E, cooling rate if other than 100 F (56 C) degrees per hour, size, and quantity. If forgings are supplied, the size and melt source of stock used to make the forgings shall also be included.

4.5 Resampling and Retesting

Shall be in accordance with the following:

4.5.1 Bars and Forging Stock

AMS 2371.

4.5.2 Forgings

AMS 2374.

5. PREPARATION FOR DELIVERY

5.1 Sizes

Except when exact lengths or multiples of exact lengths are ordered, bars will be acceptable in mill lengths of 6 to 20 feet (1.8 to 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).

5.2 Identification

Shall be as follows:

5.2.1 Bars

In accordance with AMS 2806.

5.2.2 Forgings

In accordance with AMS 2808.

5.2.3 Forging Stock

As agreed upon by purchaser and vendor.

5.3 Packaging

The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT

A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS

Product not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.

8. NOTES

8.1 A change bar (I) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this specification. An (R) symbol to the left of the document title indicates a complete revision of the specification, including technical revisions. Change bars and (R) are not used in original publications, nor in specifications that contain editorial changes only.

8.2 Annealing of fabricated parts is required to produce the required magnetic properties. Dry hydrogen atmosphere is typically recommended. Vacuum or other protective atmospheres may produce magnetic properties that are not equivalent to those produced in dry hydrogen.

8.3 Hardness conversion tables for metals are presented in ASTM E 140.

8.4 Terms used in AMS are clarified in ARP1917.

8.5 Dimensions in inch/pound units and the Fahrenheit temperatures are primary; dimensions in SI units and the Celsius temperatures are shown as the approximate equivalents of the primary units and are presented only for information.

8.6 Purchase documents should specify not less than the following: