

Tube, Aluminum Alloy, Drawn, Seamless, 5052

RATIONALE

AMS-WW-T-700/4A has been reaffirmed to comply with the SAE five-year review policy.

NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of September, 2007. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those specifications which have previously been widely used and which may be required for production or processing of existing designs in the future. The Aerospace Materials Division, however, does not recommend these specifications for future use in new designs. "NONCURRENT" specifications are available from SAE upon request.

Similar but not necessarily identical products are covered in the following specifications. However, this listing is provided for information only and does not constitute authority to substitute these specifications for the "NONCURRENT" specification.

AMS 4069D	Aluminum Alloy, Drawn, Round Seamless Tubing Close Tolerance 2.5Mg - 0.25Cr (5052-0) Annealed
AMS 4070L	Aluminum Alloy, Drawn, Round Seamless Tubing 2.5Mg - 0.25Cr (5052-0) Annealed
AMS 4071L	Aluminum Alloy, Drawn, Round, Seamless Hydraulic Tubing 2.5Mg - 0.25Cr (5052-0) Annealed
ASTM B 210	Aluminum and Aluminum-Alloy Drawn Seamless Tubes - designating alloy 5052 and applicable temper

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMSWWT700/4A>**

NOTICE

This document has been taken directly from U.S. Military Specification WW-T-700/4F, Amendment 1, and contains only minor editorial and format changes required to bring it into conformance with the publishing requirements of SAE technical standards. The initial release of this document is intended to replace WW-T-700/4F, Amendment 1. Any part numbers established by the original specification remain unchanged.

The original Military Specification was adopted as an SAE standard under the provisions of the SAE Technical Standards Board (TSB) Rules and Regulations (TSB 001) pertaining to accelerated adoption of government specifications and standards. TSB rules provide for (a) the publication of portions of unrevised government specifications and standards without consensus voting at the SAE Committee level, and (b) the use of the existing government specification or standard format.

Under Department of Defense policies and procedures, any qualification requirements and associated qualified products lists are mandatory for DOD contracts. Any requirement relating to qualified products lists (QPL's) has not been adopted by SAE and is not part of this SAE technical document.

SAENORM.COM : Click to view the full PDF of AMS-WW-T-700/4A

The complete requirements for procuring seamless tube drawn from aluminum alloy 5052 described herein shall consist of this document and the latest issue of WW-T-700/GEN (see 2.1).

1. SCOPE AND CLASSIFICATION:

1.1 Scope:

This specification covers the specific requirements for seamless tube drawn from aluminum alloy 5052.

1.2 Classification:

1.2.1 Tempers: The drawn seamless tube shall be of the following tempers: 0, H32, H34, H36, H38, and F, as specified (see 6.2 and 6.3). The definition of these tempers shall be as specified in WW-T-700/GEN.

1.2.2 Types: The tube shall be of the following types:

Type	Appearance
I -	Round
II -	Rectangular and square
III -	Streamline
IV -	Oval
V -	Odd shapes

2. APPLICABLE DOCUMENTS:

The issues of the following documents, in effect on date of invitation for bids or solicitation for offers, form a part of this specification to the extent specified herein.

2.1 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

WW-T-700/GEN Tube, Aluminum and Aluminum Alloy, Drawn, Seamless, General Specification for

(Activities outside the Federal Government may obtain copies of Federal specifications, standards, and commercial item descriptions, as outlined under General Information in the Index of Federal Specifications, Standards and Commercial Item Descriptions. The Index, which includes cumulative bimonthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

2.1 (Continued):

(Single copies of this specification and other Federal specifications and commercial item descriptions required by activities outside the Federal Government for bidding purposes are available without charge from the General Services Administration Business Service Centers in Boston, MA; New York, NY; Philadelphia, PA; Washington, DC; Atlanta, GA; Chicago, IL; Kansas City, MO; Fort Worth, TX; Houston, TX; Denver, CO; San Francisco, CA; Los Angeles, CA; and Seattle, WA.

(Federal Government activities may obtain copies of Federal standardization documents and the Index of Federal Specifications, Standards, and Commercial Item Descriptions from established distribution points in their agencies.)

3. REQUIREMENTS:

3.1 Chemical composition:

The chemical composition shall conform to the requirements specified in Table I.

TABLE I. Chemical composition ^{1/}

Element	Percent	
	Minimum	Maximum
Silicon plus iron	—	0.45
Copper	—	0.10
Manganese	—	0.10
Magnesium	2.2	2.8
Chromium	0.15	0.35
Zinc	—	0.10
Others, each	—	0.05
Other, total ^{2/}	—	0.15
Aluminum	Remainder	

^{1/} Except for "Aluminum" and "Others", analysis normally is made for elements for which specific limits are shown

^{2/} The sum of those "Others" metallic elements 0.010 percent or more each, expressed to the second decimal before determining the sum

3.2 Mechanical properties:

- 3.2.1 Tensile and yield strength: The tensile and yield strength mechanical properties parallel to the direction of drawing shall be as specified in table II.