


SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

REV. A	FEDERAL SUPPLY CLASS 5306	
	THE INITIAL SAE PUBLICATION OF THIS DOCUMENT WAS TAKEN DIRECTLY FROM U.S. MILITARY STANDARD MS9219, NOTICE 1. THIS SAE STANDARD RETAINS THE SAME PART NUMBERS ESTABLISHED BY THE ORIGINAL MILITARY DOCUMENT. ANY REQUIREMENTS ASSOCIATED WITH QUALIFIED PRODUCTS LISTS (QPL) MAY CONTINUE TO BE MANDATORY FOR DOD CONTRACTS. REQUIREMENTS RELATING TO QPL'S HAVE NOT BEEN ADOPTED BY THE SAE FOR THIS STANDARD AND ARE NOT PART OF THIS SAE DOCUMENT. WARNING THIS DOCUMENT INCLUDES CADMIUM AS A PLATING MATERIAL. THE USE OF CADMIUM HAS BEEN RESTRICTED AND/OR BANNED FOR USE IN MANY COUNTRIES DUE TO ENVIRONMENTAL AND HEALTH CONCERNS. THE USER SHOULD CONSULT WITH LOCAL OFFICIALS ON APPLICABLE HEALTH AND ENVIRONMENTAL REGULATIONS REGARDING ITS USE.	
AS9219	THIRD ANGLE PROJECTION 	
PREPARED BY SAE COMMITTEE E-25, GENERAL STANDARDS FOR AEROSPACE AND PROPULSION SYSTEMS		
	AEROSPACE STANDARD (R) BOLT, MACHINE - STEEL, DIFFUSED NICKEL-CADMIUM PLATED, DOUBLE HEXAGON EXTENDED WASHER HEAD, DRILLED, UNS K14675, 195 KSI MIN, .3125-24 UNJF-3A	AS9219 SHEET 1 OF 4 REV. A

SAENORM.COM : Click to view the full PDF of as9219

ISSUED 2000-08 REVISED 2002-05




FIGURE 1 - BOLT

REV.
A

AS9219

TABLE 1 - PART NUMBERS AND DIMENSIONS

PART NO.	L	K	APPROX. MASS LB/100	PART NO.	L	K	APPROX. MASS LB/100
MS9219-04	.500	.088 - .108	2.06	MS9219-34	3.000	2.065 - 2.125	6.58
MS9219-05	.562	.088 - .108	2.17	MS9219-35	3.125	2.190 - 2.250	6.80
MS9219-06	.625	.088 - .108	2.28	MS9219-36	3.250	2.315 - 2.375	7.03
MS9219-07	.688	.088 - .108	2.39	MS9219-37	3.375	2.440 - 2.500	7.27
MS9219-08	.750	.088 - .108	2.51	MS9219-38	3.500	2.565 - 2.625	7.50
MS9219-09	.812	.088 - .108	2.62	MS9219-39	3.625	2.690 - 2.750	7.73
MS9219-10	.875	.088 - .108	2.73	MS9219-40	3.750	2.815 - 2.875	7.95
MS9219-11	.938	.088 - .108	2.85	MS9219-41	3.875	2.940 - 3.000	8.17
MS9219-12	1.000	.125 - .145	2.96	MS9219-42	4.000	3.065 - 3.125	8.40
MS9219-13	1.062	.128 - .188	3.07	MS9219-43	4.125	3.190 - 3.250	8.63
MS9219-14	1.125	.190 - .250	3.19	MS9219-44	4.250	3.315 - 3.375	8.86
MS9219-15	1.188	.252 - .312	3.30	MS9219-45	4.375	3.440 - 3.500	9.08
MS9219-16	1.250	.315 - .375	3.41	MS9219-46	4.500	3.565 - 3.625	9.30
MS9219-17	1.312	.378 - .438	3.52	MS9219-47	4.625	3.690 - 3.750	9.52
MS9219-18	1.375	.440 - .500	3.64	MS9219-48	4.750	3.815 - 3.875	9.74
MS9219-19	1.438	.502 - .562	3.75	MS9219-49	4.875	3.940 - 4.000	9.95
MS9219-20	1.500	.565 - .625	3.87	MS9219-50	5.000	4.065 - 4.125	10.17
MS9219-21	1.562	.628 - .688	3.98	MS9219-51	5.125	4.190 - 4.250	10.40
MS9219-22	1.625	.690 - .750	4.10	MS9219-52	5.250	4.315 - 4.375	10.63
MS9219-23	1.688	.752 - .812	4.22	MS9219-53	5.375	4.440 - 4.500	10.86
MS9219-24	1.750	.815 - .875	4.33	MS9219-54	5.500	4.565 - 4.625	11.10
MS9219-25	1.875	.940 - 1.000	4.55	MS9219-55	5.625	4.690 - 4.750	11.33
MS9219-26	2.000	1.065 - 1.125	4.77	MS9219-56	5.750	4.815 - 4.875	11.56
MS9219-27	2.125	1.190 - 1.250	5.00	MS9219-57	5.875	4.940 - 5.000	11.78
MS9219-28	2.250	1.315 - 1.375	5.23	MS9219-58	6.000	5.065 - 5.125	12.00
MS9219-29	2.375	1.440 - 1.500	5.45				
MS9219-30	2.500	1.565 - 1.625	5.67				
MS9219-31	2.625	1.690 - 1.750	5.90				
MS9219-32	2.750	1.815 - 1.875	6.13				
MS9219-33	2.875	1.940 - 2.000	6.36				

NOTES:

1. MATERIAL: LOW ALLOY STEEL AMS 6304 (UNS K14675).
2. PROCUREMENT SPECIFICATION: AS7459.
3. HARDNESS: 42-46 HRC.
4. FINISH: DIFFUSED NICKEL-CADMIUM PLATE AMS 2416. DIMENSIONS ARE AFTER PLATING. CONTACT POINTS PERMISSIBLE. PD MAY BE REDUCED .0012 MAXIMUM BEFORE PLATING.
5. MAGNETIC PARTICLE INSPECTION PER ASTM E 1444 BEFORE PLATING.
6. INCOMPLETE THREADS NOT TO ENTER FILLET.
7. SURFACE TEXTURE: SYMBOLS PER ASME Y14.36M. REQUIREMENTS PER ASME B46.1. UNLESS OTHERWISE SPECIFIED, SURFACES TO BE 125 MICROINCHES Ra EXCEPT UPSET HEAD.
8. BREAK SHARP EDGES .003-.015, UNLESS OTHERWISE SPECIFIED.
9. DIMENSIONING AND TOLERANCING PER ANSI Y14.5M-1982 (ASME PUBLICATION).
10. DIMENSIONS IN INCHES. UNLESS OTHERWISE SPECIFIED, TOLERANCES: LINEAR DIMENSIONS $\pm .010$, ANGULAR DIMENSIONS $\pm 5^\circ$.
11. DO NOT USE UNASSIGNED PART NUMBERS.

AEROSPACE STANDARD

(R)

BOLT, MACHINE - STEEL, DIFFUSED NICKEL-
CADMIUM PLATED, DOUBLE HEXAGON
EXTENDED WASHER HEAD, DRILLED, UNS K14675,
195 KSI MIN, .3125-24 UNJF-3A

AS9219
SHEET 3 OF 4

REV.
A